

染色堅牢度データ表

ルミエスタ LS-2500

カラーNO	耐光(級)	洗濯(級)			汗(級)						摩擦(級)		ドライクリーニング	
	JIS L-0842	JIS L-0844 A-2法			JIS L-0848 A法						JIS L-0849		JIS L-0860A 石油系	
	第3露光法	変退色	汚染		酸性			アルカリ性			乾燥	湿潤	変退色	汚染
	3,4級試験		綿	ナイロン	変退色	汚染		変退色	汚染					
			綿	ナイロン	変退色	綿	ナイロン	変退色	綿	ナイロン				
LS1001	3	4-5	5	5	5	5	5	5	5	5	5	5	5	5
LS1002	4	4-5	5	5	5	5	5	5	5	5	5	4-5	5	5
LS1003	4	4-5	5	5	5	5	5	5	5	5	5	4-5	5	5
LS1004	4	4-5	5	5	5	5	5	5	5	5	5	5	5	5
LS1005	4	4-5	5	5	5	5	5	5	5	5	5	4-5	5	5
LS1006	4	5	5	5	5	5	5	5	5	5	5	4-5	5	5
LS1007	4	4-5	5	5	5	5	5	5	5	5	5	4-5	5	5
LS1008	4	4-5	5	5	5	5	5	5	5	5	4-5	4-5	4-5	5
LS1009	4	4-5	4-5	5	5	5	5	5	5	5	4-5	3	5	5
LS1010	4	4-5	4-5	5	5	5	5	5	5	5	4-5	2-3	4-5	5
LS1011	4	4-5	5	5	5	5	5	5	5	5	5	5	5	5
LS1012	4	4-5	5	5	5	5	5	5	5	5	4-5	4	4-5	5
LS1013	4	4-5	5	5	5	5	5	5	5	5	4-5	4	5	5
LS1014	4	4-5	4-5	5	5	5	5	5	5	5	4-5	2-3	4-5	5
LS1015	4	4-5	4-5	5	5	5	5	5	5	5	4-5	2-3	4-5	4-5
LS1016	4	4-5	5	5	5	5	5	5	5	5	5	4-5	4-5	5
LS1017	4	4-5	5	5	5	5	5	5	5	5	5	5	4-5	5
LS1018	4	4-5	5	5	5	5	5	5	5	5	4-5	4-5	4-5	5
LS1019	4	4-5	5	5	5	5	5	5	5	5	5	4-5	4-5	5
LS1020	3-4	4-5	5	5	5	5	5	5	5	5	5	4	5	5
LS1021	4	4-5	5	5	5	5	5	5	5	5	5	5	4-5	5
LS1022	4	4-5	5	5	5	5	5	5	5	5	5	5	5	5
LS1023	4	4-5	5	5	5	5	5	5	5	5	5	4-5	5	5
LS1024	4	4-5	5	5	5	5	5	5	5	5	4-5	4-5	4-5	5
LS1025	4	4-5	5	5	5	5	5	5	5	5	4-5	4-5	4-5	5
LS1026	4	4-5	5	5	5	5	5	5	5	5	5	5	5	5
LS1027	4	4-5	5	5	5	5	5	5	5	5	5	5	5	5
LS1028	4	4-5	5	5	5	5	5	5	5	5	5	4-5	5	5
LS1029	3-4	4-5	5	5	5	5	5	5	5	5	4-5	3	4-5	5
LS1030	4	4-5	4-5	5	5	5	5	5	5	5	4-5	2-3	4-5	5