

染色堅牢度データ表

ソフィア MDX-1300

カラ-NO	耐光(級)	洗濯(級)			汗(級)						摩擦(級)		ドライクリーニング	
	JIS L-0842	JIS L-0844 A-2法			JIS L-0848 A法						JIS L-0849		JIS L-0860 A 石油系	
	第3露光法	変退色	汚染		酸性			アルカリ性			乾燥	湿潤	変退色	汚染
	3,4級試験		綿	ナイロン	変退色	汚染		変退色	汚染					
					綿	ナイロン		綿	ナイロン					
MDX999	3-4	4-5	5	5	5	5	5	4-5	5	5	5	5	5	5
MDX000	3-4	4-5	5	5	5	5	5	5	5	5	5	5	4-5	5
MDX001	4	4-5	5	5	5	5	5	5	5	5	5	4-5	4-5	5
MDX002	4	5	5	5	5	5	5	5	5	5	5	5	5	5
MDX003	4以上	4-5	5	5	5	5	5	5	5	5	4-5	4-5	4-5	5
MDX004	3-4	4-5	5	5	5	5	5	5	5	5	5	4-5	4-5	5
MDX006	4以上	4-5	5	4-5	5	5	5	5	5	5	5	5	5	4-5
MDX008	4	4-5	5	5	5	5	5	5	5	5	4-5	4-5	5	5
MDX009	4	4-5	5	5	5	5	5	5	5	5	5	5	5	5
MDX010	4	4	5	5	5	5	5	5	5	5	5	5	5	5
MDX011	4	5	5	4-5	5	5	5	5	5	5	5	5	5	5
MDX012	4	4-5	5	5	5	5	5	5	5	5	4-5	4-5	4-5	5
MDX013	4以上	4-5	5	5	5	5	5	5	5	5	4-5	4-5	5	5
MDX014	4以上	4-5	4-5	4-5	5	4-5	4-5	5	4-5	4-5	4	4-5	5	4-5
MDX016	4以上	4-5	4-5	4-5	5	4-5	4-5	5	4-5	4-5	4	4-5	5	4-5
MDX019	4以上	5	5	5	5	5	5	5	5	5	5	5	5	5
MDX022	4	4-5	5	5	5	5	5	5	5	5	4-5	4-5	5	5
MDX023	4	4-5	5	5	5	5	5	5	5	5	5	5	5	5
MDX024	4以上	4-5	4-5	4-5	5	4-5	4-5	5	4-5	4-5	4	4-5	5	4-5
MDX025	4	5	5	5	5	4-5	4-5	5	4-5	4-5	5	5	5	5
MDX026	4	5	5	5	5	4-5	4-5	5	4-5	4-5	5	5	5	5
MDX027	4以上	4-5	5	5	5	5	5	5	5	5	4-5	4-5	5	5
MDX028	4以上	4-5	5	4-5	5	5	5	5	5	5	4-5	4-5	4-5	5
MDX029	4以上	4-5	5	5	5	5	5	5	5	5	5	5	4-5	5
MDX030	4以上	5	5	5	5	5	5	5	5	5	4-5	5	5	5
MDX031	4以上	5	4-5	4-5	5	4-5	4-5	5	4-5	4-5	4	3	5	5
MDX032	4以上	4-5	4-5	4-5	5	5	4-5	5	4-5	4-5	3-4	4-5	4-5	4-5
MDX033	4	4	5	5	5	5	5	5	5	5	5	5	4-5	5
MDX034	4	4-5	5	5	5	5	5	4-5	5	5	5	5	5	5
MDX035	4以上	5	4-5	4-5	5	4-5	4-5	5	4-5	4-5	4	4-5	5	4-5
MDX036	4以上	5	5	5	5	5	5	5	5	5	3-4	4-5	5	5