

カラーNO	耐光(級)	洗濯(級)			汗(級)						摩擦(級)		ドライクリーニング*	
	JIS L-0842	JIS L-0844 A-1法			JIS L-0848 A法						JIS L-0849		JIS L-0860 A 石油系	
	第3露光法	変退色	汚染		変退色	酸性		変退色	アルカリ性		乾燥	湿潤	変退色	汚染
	3,4級試験		綿	ナイロン		綿	ナイロン		綿	ナイロン				
RS001	4	5	5	5	5	5	5	5	5	5	5	5	5	5
RS002	4以上	5	5	5	5	5	5	5	5	5	5	5	5	5
RS003	4以上	5	5	5	5	5	5	5	5	5	5	5	5	5
RS004	4以上	5	5	5	5	5	5	5	5	5	5	5	5	5
RS005	4以上	5	5	5	5	5	5	5	5	5	5	5	5	5
RS006	4以上	5	5	5	5	5	5	5	5	5	5	5	5	5
RS007	4以上	5	5	5	5	5	4	5	4-5	3-4	5	4-5	5	5
RS008	4以上	5	5	5	5	5	5	5	5	5	5	5	5	5
RS009	4以上	5	5	5	5	5	4-5	5	5	4-5	5	5	5	5
RS010	4以上	5	5	5	5	5	5	5	5	5	5	5	5	5
RS011	4以上	5	5	5	5	5	5	5	5	4-5	4-5	4-5	5	5
RS012	4以上	5	4-5	4-5	5	4-5	3-4	5	4	3-4	4-5	4	5	4-5
RS013	4以上	5	5	5	5	5	5	5	5	5	5	5	5	5
RS014	4以上	5	5	5	5	5	5	5	5	5	5	5	5	5
RS015	4以上	5	5	5	5	5	5	5	5	5	5	5	5	5
RS016	4以上	5	5	5	5	5	5	5	5	5	5	5	5	5
RS017	4	4-5	5	5	5	5	5	5	5	5	5	5	5	5
RS018	4以上	4-5	5	5	5	5	5	5	5	4-5	5	5	5	5
RS019	4	5	5	5	5	5	5	5	5	5	5	5	5	5
RS020	4以上	5	5	5	5	5	5	5	5	5	5	4-5	5	5
RS021	4以上	5	5	4-5	5	4-5	4	5	4-5	3-4	4-5	4	5	4-5
RS022	4	5	4-5	4-5	5	4-5	4-5	5	4-5	4	4	3-4	5	4-5
RS023	3-4	5	4-5	4-5	5	5	4-5	5	5	4-5	5	3-4	5	4-5
RS024	3-4	5	4-5	4-5	5	4-5	4-5	5	4-5	4	4-5	3-4	5	4-5
RS025	4	4-5	5	5	5	5	5	5	5	5	5	5	5	5
RS026	4以上	5	4-5	4-5	5	4-5	4-5	5	4-5	4-5	5	4-5	5	5
RS027	4以上	5	5	5	5	5	5	5	5	5	5	4	5	5
RS028	4以上	5	4-5	4-5	5	4-5	4-5	5	4-5	4-5	5	4-5	5	5
RS029	4以上	5	4-5	4-5	5	4-5	4-5	5	4-5	4-5	4-5	3-4	5	5
RS030	4以上	5	4-5	4-5	5	4-5	4-5	5	4-5	4	5	4	5	5
RS031	4以上	5	4-5	4-5	5	4-5	4-5	5	4-5	4-5	4-5	2-3	5	5
RS032	4以上	5	4-5	4-5	5	4-5	4-5	5	4-5	4-5	4-5	2-3	5	4-5