

染色堅牢度表

2021/02/18

FN-300

カラーNO.	耐光性	洗濯			汗						摩擦		ドライクリーニング	
	JIS L0842	JIS L0844 A-2			JIS L0848						JIS L0849 試験機Ⅱ		JIS L0860 A法石油系	
	第3露光法				酸			アルカリ						
	3,4級試験	変退色	汚染 綿	汚染 ナイロン	変退色	汚染 綿	汚染 ナイロン	変退色	汚染 綿	汚染 ナイロン	乾燥	湿潤	変退色	汚染
FN606	4	5	5	5	5	5	5	5	5	5	4-5	4-5	5	5
FN608	4以上	5	5	5	5	5	5	5	5	5	4-5	4	5	5
FN610	4以上	5	5	5	5	5	5	5	5	5	4-5	4	5	5
FN611	4	5	5	5	5	5	5	5	5	5	5	4-5	5	5
FN612	4	5	5	5	5	5	5	5	5	5	5	4-5	5	5
FN618	4以上	5	5	4-5	5	5	4-5	5	5	4-5	4-5	4	5	5
FN624	4以上	5	5	5	5	5	5	5	5	5	4-5	4-5	5	5
FN632	4以上	5	5	5	5	5	5	5	5	5	4-5	4-5	5	5
FN640	4以上	5	4-5	4-5	5	4-5	4-5	5	4-5	4-5	4-5	2-3	5	5
FN643	4以上	5	5	5	5	4-5	4-5	5	4-5	4-5	4-5	4	5	5
FN655	4以上	5	5	5	5	4-5	4-5	5	4-5	4-5	4-5	4-5	5	5
FN663	4以上	5	4-5	4-5	5	4-5	4-5	5	4-5	4-5	4-5	2	5	5
FN666	4以上	5	5	5	5	5	5	5	5	5	4-5	4	5	5
FN669	4以上	5	4-5	4-5	5	5	5	5	5	5	4	3	5	5
FN701	4以上	5	4-5	4-5	5	4-5	4-5	5	4-5	4-5	4-5	2-3	5	4-5
FN702	4以上	5	4-5	4-5	5	4-5	4-5	5	4-5	4-5	4-5	2	5	4-5
FN703	4	5	4	4-5	5	4-5	4-5	5	4-5	4-5	4	2	5	4-5
FN704	4以上	4-5	4-5	4-5	5	4	4	5	4	4	4	2	4-5	4-5
FN705	4	4-5	5	5	5	5	5	5	5	5	4-5	4-5	5	5
FN706	4	5	4-5	4-5	5	4-5	4-5	5	4-5	4-5	4-5	2-3	5	5
FN707	4以上	5	4-5	4-5	5	4-5	4	5	4	4	4	2	5	4-5
FN6021	4以上	4-5	5	5	5	5	5	5	5	5	4-5	4-5	5	5
FN6022	4以上	5	5	5	5	5	5	5	5	5	4-5	4-5	5	5
FN6614	4以上	5	4-5	4-5	5	5	5	5	5	5	4-5	2	5	5
FN6084	4以上	4-5	5	5	5	5	5	5	5	5	4-5	4-5	5	5
FN6023	4以上	5	5	5	5	5	5	5	5	5	5	5	5	5
FN6634	4以上	5	4-5	4-5	5	4-5	4-5	5	4-5	4-5	4-5	2	5	5

BRIGHTEX

クラウン工業(株)